

REPRO★LON

Technical Data Sheet

100% Virgin PTFE Sheet

NON-FREE FLOW POLYTETRAFLUOROETHYLENE

SPECIFIC GRAVITY :	ASTM: D-792-08	G/ CC	2.160-2.250 Max
TENSILE STRENGTH :	D-4745-11a	PSI	2000 Min.
ELONGATION :	D-4745-11a	%	250% Min.
SHORE HARDNESS D:	D-785	D	58-62
THICKNESS TOLERANCES:	D-3308-12	in.	.0151" - .0400" = .0015" Tolerance .0401" - .1250" = .0050" Tolerance.

Certs are available upon request. These are typical properties and as such should not be used for specification purposes.

This information is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We cannot guarantee favorable results and assume no liability in connection with its use of the product described. None of this information is to be taken as a license to operate under, or a recommendation to infringe any patents. The use of this product should be determined by the user, based on their appraisal.

[Repro-Lon](#)

203 Repro Drive

Burnet, TX 78611

(512) 756-2410

www.repro-lon.com